

SPECIFICATION		PAGE	1/3
PART NUMBER :	TDX331060	REV.	A

**SPECIFICATION**

**PART NO:           TDX331060**

【Approval Stamp Column 】

Customer :



**STODA Technologies(Shantou)LTD**

**Tel : 0754-89918282**

**Website: [www.stodatech.com](http://www.stodatech.com)**

**Email: [sales@stodatech.com](mailto:sales@stodatech.com)**

**Address: Huanshi east road, Chen nan street , Chaoyang , Shan tou, Guang dong P.R.C**

SPECIFICATION		PAGE	2/3
PART NUMBER :	TDX331060	REV.	A

1: PHYSICAL DIMENSION

BEFORE COATING


OUTSIDE DIAMETER	(OD)	:	33.02	mm	MAX
INSIDE DIAMETER	(ID)	:	19.94	mm	MIN
HEIGHT	(HT)	:	8.76	mm	MAX

AFTER COATING :

OUTSIDE DIAMETER	(OD)	:	33.83	mm	MAX
INSIDE DIAMETER	(ID)	:	19.3	mm	MIN
HEIGHT	(HT)	:	9.70	mm	MAX


2: CORE MAGNETIC PARAMETERS

EFFECTIVE MAGNETIC PATH LENGTH	(L <sub>e</sub> )	:	8.147	cm
EFFECTIVE CROSS SEPCION AREA	(A <sub>e</sub> )	:	0.551	cm <sup>2</sup>
EFFECTIVE VOLUME	(V <sub>e</sub> )	:	4.49	cm <sup>3</sup>



3: DC BIASED INDUCTANCE


H <sub>DC</sub>	:	100	Oe
PERCENT INITIAL PERM(NOM)	:	57.79%	
PERCENT INITIAL PERM(MIN. )	:	50.66%	



SPECIFICATION		PAGE	3/3
PART NUMBER :	TDX331060	REV.	A

#### 4: CORE LOSS

$B_{pk}$  : 1000 G  
 FREQUENCY : 50 kHz  
 CORE LOSS (NOMINAL) : 120 mW/cm<sup>3</sup>  
 CORE LOSS (MAXIMUM) : 140 mW/cm<sup>3</sup>



#### 5: INDUCTANCE

$\mu_i$  (REFERENCE) : 60  
 AL VALUE (NOMINAL) : 51 nH/N<sup>2</sup>  
 FREQUENCY : 10kHz  
 VOLTAGE ON TH2829A : 0.29V  
 AL TOLERANCE :  $\pm 8\%$   
 TEST INSTRUMENT : TH2829A

#### 6: COATING/PACKAGE

COATING TYPE : Black Epoxy  
 VOLTAGE BREAKDOWN (MIN.) : 1000 Vrms  
 LIMIT : 0.1 mA, 5 s  
 PACKAGE QUANTITY : 576 Pcs/Box

#### 7: MATERIAL DESCRIPTION

85%Fe, 9%Si, 6%Al

REVISION HISTORY			PREPARED	CHECKED	APPROVED
REV.	DESCRIPTION	DATE			
A	FIRST ISSUE	2022/6/8			